

## NEMA GRADE G-9 GLASS MELAMINE

Arc Chutes and Barriers  
Terminal Boards

Receptacle Plates  
Bus tube Insulation

Colours: Natural Brown, White

### Physical Properties

Specific Gravity	gm / cc			1.80
Tensile Strength	PSI	lengthwise		12,000
Tensile Strength	PSI	crosswise		10,000
Compressive Strength	PSI	flatwise		70,000
Flexural Strength	PSI	lengthwise		60,000
Flexural Strength	PSI	crosswise		50,000
Hardness	Rockwell (M)			120
Water Absorption	%	24 hrs	0.062 th	0.60
			0.125 th	0.35
			0.500 th	0.20
Heat Resistance / Maximum Constant Operating Temp				280 F

### Electrical Properties

Dielectric Strength	VMP	Perpendicular	0.062 th	350
			0.125 th	260
Dielectric Constant	1 Mhz	Condition A		7.8

Grade G-9 is a Glass Melamine laminate with high Mechanical and Electrical values, particularly in high moisture conditions and generally where high arc- and track resistance is required.

Values are based on typical Test Methods and Conditions and published for Reference purposes only